

OUTLOOK MODE



SOLAR OPTICAL PROPERTIES						SHADING COEFFICIENT	
COLOUR	ULTRAVIOLET TRANSMISSION % (TUV)	SOLAR TRANSMITTANCE % (TS)	SOLAR REFLECTANCE % (RS)	SOLAR ABSORPTANCE % (AS)	VISUAL TRANSMITTANCE % (TV)	3MM GLASS	6MM GLASS
517 Chalk	7	11	76	13	15	0.09	0.09
572 Porcelain	6	10	65	25	12	0.10	0.09
508 Nougat	6	10	49	41	11	0.15	0.15
529 Wheat	5	4	48	48	10	0.08	0.08
575 Marzipan	6	5	69	23	11	0.08	0.08
566 Alpaca	6	4	47	49	9	0.08	0.08
504 Spice	6	1	16	83	5	0.10	0.10
511 Macchiato	7	9	16	75	12	0.18	0.18
533 Mocha	7	4	35	61	11	0.10	0.10
555 Bronze	6	1	11	88	9	0.11	0.11
597 Maroon	8	3	16	81	10	0.11	0.11
565 Arctic Blue	6	2	13	85	9	0.11	0.11
506 Navy	5	2	11	87	8	0.11	0.11
503 Deep Sea	6	1	8	91	4	0.11	0.11
582 Celedon	6	8	30	62	14	0.13	0.12
559 Forest Green	5	2	9	89	8	0.12	0.12
526 Greystone	8	4	49	47	9	0.06	0.06
564 Platinum	6	5	42	53	10	0.09	0.09
507 Bamboo	6	6	16	78	9	0.15	0.15
505 Silver Sky	6	2	27	71	7	0.10	0.09
551 Ash	5	2	17	81	8	0.11	0.11
544 Eclipse▼	7	3	12	85	10	0.12	0.12
510 Moonlight	7	8	10	82	12	0.18	0.18
509 Flint▼	7	6	5	89	10	0.16	0.16
553 Blackstone▼	5	1	8	91	8	0.11	0.11
539 Shale Grey®*	4	8	43	49	8	0.14	0.14
540 Woodland Grey®*	5	6	13	81	8	0.16	0.15
541 Basalt®*	5	5	13	82	7	0.15	0.15
542 Monument®*	5	5	8	87	7	0.15	0.15

Tested at a 30 degree profile angle. ▼ Selected Colours. * Inspired by COLORBOND®

APPLICATIONS	Exterior roll-up shades and awnings
ROLL WIDTH	220cm▼, 275cm & 320cm
ROLL LENGTH	30 metres
NOMINAL WEIGHT	540gsm
FABRIC TYPE	PVC coated polyester mesh
COMPOSITION	28% polyester / 72% vinyl on polyester
LIGHT FASTNESS	6-7
OPENNESS FACTOR	5%
FABRIC THICKNESS	0.81mm
TREATMENT	UV stabilised, fire retardant, Microban antimicrobial treatment, Greenguard Gold certified and LeadFree * Independant test results available by request

Shading Coefficient

The solar optical properties are used to calculate the shading coefficient. The shading coefficient represents the percentage of solar heat gain that is transmitted to the interior through the glass and shading system. Darker colours provide maximum glare reduction and visibility. A lower number means higher protection from the incoming heat. The rating used for this is a scale of 0-1.

Fire Retardant - AS1530.3 - 1999

Outlook fabrics are manufactured by Phifer Inc in their state of the art facilities. Independent laboratory testing shows that Outlook fabrics meet or exceed flame retardancy requirements.

Ignitability Index	16	(Range 0-20)
Spread of Flame Index	0	(Range 0-10)
Heat Evolved Index	2	(Range 0-10)
Smoke Developed Index	8	(Range 0-10)